

Technical Literature E-03

Arc Resistance and Dielectric Breakdown Strength of AURUM[®]

The Table below shows results of the measurement of the arc resistance and dielectric breakdown strength of AURUM[®].

Grade	Arc resistance (Sec)	Dielectric breakdown strength (KV/mm)
Natural 450	81	16.6
JGN3030	91	21.1

The information contained herein is based on the information and data available at this moment, but none of the data or evaluation results contained herein provide any warranty whatsoever.