

Product name	Resin constant value				Room temp. drying		Pencil hardness (7days)	Features	Applications
	NV (%)	Vis (mPa·s/25°C)	pH	AV	Set to touch (min)	Thorough dry (min)			
UD100N	30	30~100	8	25	40	120	B	General purpose	General purpose
UD111N	30	50~200	7.5	40	45	120	B	Printing ink	High acid value

NV: Non-volatile Vis: Viscosity